

Rosewool Insulation Refractory Co.,Ltd

Add.:No366,Nanmixin Road, Xinmi City, Zhengzhou,Henan, China

Tel: +86-371-63395502

High Denstiy Calcium Silicate Board

Item	Unit	Index
Bulk Density	Kg/m ³	850-950
Max. Temperature	°C	1000-1100
Rupture Strength	Mpa	≥6.5
Compressive Strength	Mpa	≥ 12
Linear Shrinkage	%	≤ 1
Thermal Conductivity (W/m.k)	100°C	0.113
	200°C	0.120
	300°C	0.121
	400°C	0.125